

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 09-260124

(43)Date of publication of application : 03.10.1997

(51)Int.Cl.

H01F 1/11

C01G 49/00

C04B 35/26

H01F 41/02

(21)Application number : 08-097777

(71)Applicant : SUMITOMO SPECIAL METALS CO
LTD

(22)Date of filing : 26.03.1996

(72)Inventor : TOYODA YUKIO

(54) FERRITE MAGNET AND MANUFACTURING METHOD THEREOF

(57)Abstract:

PROBLEM TO BE SOLVED: To improve the magnetic characteristics by specifying the value n which limits the compsn. range of a ferrite magnet having a basic compsn. of $\text{SrO} \cdot 2(\text{FeO}) \cdot n(\text{Fe}_2\text{O}_3)$ and adding specified additive element after/before calcining to control the pulverized grain size.

SOLUTION: A ferrite magnet has a compsn. of $\text{SrO} \cdot 2(\text{FeO}) \cdot n(\text{Fe}_2\text{O}_3)$ wherein n to limit the compsn. range meets 7.2-7.7, the mean crystal grain size of a sintered block is $2\mu\text{m}$ or less, $(\text{BH})_{\text{max}}$ is 5MGOe or more. C is added 0.3-5.0wt.% to a material powder composed of SrCO_3 and Fe_2O_3 mixed at a mol ratio of 1 to 8, the material is calcined, CaO 0.3-1.5wt.%, SiO_2 0.1-0.6wt.%, and C 0.1-0.5wt.% are added, it is pulverized to a mean grain size of $0.06\mu\text{m}$ or less, and the obtained powder is formed in a magnetic field and sintered in a nonoxidative atmosphere to produce a ferrite magnet. Thus, a W type ferrite is easily obtained at low cost.

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office